http://www.jourmag.org/index.php/jma

Journal of Magnetism and Its Applications

Received December 29th 2024 received in revised January 6th 2025 accepted January 12th 2025

Research articles

Magnetocaloric Materials for Efficient Cooling Technologies

Wei Zhang
Institute of Advanced Functional Materials, Tsinghua University, China

Article info

Keywords:
Magnetocaloric effect,
magnetic refrigeration,
rare-earth alloys,
entropy change,
magnetic materials,
solid-state cooling,
energy-efficient refrigeration,
thermal management

Abstract

Magnetocaloric materials have emerged as promising candidates for next-generation cooling technologies due to their ability to convert magnetic energy into thermal energy through the magnetocaloric effect (MCE). These materials exhibit temperature changes when subjected to external magnetic fields, enabling environmentally friendly refrigeration systems that avoid harmful greenhouse gases used in conventional vapor-compression refrigeration. Recent advances in materials science have led to the development of high-performance magnetocaloric alloys such as gadolinium-based compounds, LaFeSi alloys, and MnFeP-based materials, which exhibit significant entropy changes near room temperature. This article reviews the fundamental principles of the magnetocaloric effect, key classes of magnetocaloric materials, recent technological developments, and engineering challenges associated with magnetic refrigeration systems. It also discusses potential applications in domestic refrigeration, cryogenic cooling, and energy-efficient thermal management systems. The study highlights ongoing research efforts aimed at improving material performance, reducing costs, and enabling large-scale commercialization of magnetic refrigeration technology.

Introduction

Cooling technologies play a crucial role in modern society, supporting applications ranging from household refrigeration to industrial cryogenics. Conventional cooling systems typically rely on vapor-compression cycles that use refrigerant gases, many of which contribute to environmental issues such as global warming and ozone depletion. As a result, researchers have been exploring alternative solid-state cooling technologies that offer higher efficiency and lower environmental impact. Magnetic refrigeration based on the magnetocaloric effect (MCE) is one such promising technology. The magnetocaloric effect refers to the temperature change observed in certain magnetic materials when exposed to a varying magnetic field. When a magnetic field is applied to a magnetocaloric material, its magnetic moments align with the field, resulting in a decrease in magnetic entropy and the release of heat. When the magnetic field is removed, the material absorbs heat and cools down, enabling refrigeration cycles. The magnetocaloric phenomenon was first observed in 1881 and later developed into a practical cooling principle through research on adiabatic demagnetization and magnetic phase transitions. Advances in material science have significantly improved the performance of magnetocaloric materials, particularly those operating near room temperature, which are suitable for household and industrial refrigeration applications. Modern magnetocaloric research focuses on discovering materials with large entropy changes, minimal hysteresis, and strong magneto-thermal coupling. Examples include gadolinium and its alloys, $La(Fe,Si)_{13}$ compounds, MnFe(P,As) systems, and Heusler alloys. These materials exhibit large magnetocaloric responses near their magnetic transition temperatures, making them attractive for high-efficiency cooling technologies.

Fundamentals of the Magnetocaloric Effect

The magnetocaloric effect (MCE) is a thermodynamic phenomenon observed in magnetic materials where a change in the applied magnetic field causes a reversible change in temperature. This effect originates from the strong coupling between the magnetic ordering of atomic moments and the thermodynamic properties of the material. In magnetic solids, the magnetic moments of atoms behave like tiny dipoles. When an external magnetic field is applied, these dipoles tend to align with the direction of the field, leading to a more ordered magnetic state. This alignment reduces the magnetic entropy of the system. According to the principles of thermodynamics, a reduction in entropy under adiabatic conditions results in a rise in temperature because the energy associated with the increased magnetic order is released as heat. When the magnetic field is removed, the magnetic dipoles lose their ordered arrangement and return to a more random orientation. This process increases magnetic entropy, and the material absorbs heat from its surroundings, causing its temperature to decrease. This reversible heating and cooling process forms the fundamental basis of magnetic refrigeration, a solid-state cooling technology that does not rely on conventional gas compression cycles. The efficiency of magnetocaloric materials depends on how strongly their magnetic ordering changes with the applied magnetic field and how effectively the heat exchange process can be managed within a refrigeration cycle. Two thermodynamic parameters are commonly used to quantify the magnetocaloric performance of a material. The first parameter is the isothermal magnetic entropy change (ΔS), which measures how much the entropy of a material changes when a magnetic field is applied or removed at constant temperature. A larger entropy change generally corresponds to a stronger magnetocaloric effect and higher cooling efficiency. The second important parameter is the adiabatic temperature change ($\Delta T_a d$), which represents the actual temperature variation of the material when the magnetic field is changed under adiabatic conditions. Materials exhibiting large values of both ΔS and $\Delta T_a d$ are considered ideal candidates for magnetic refrigeration applications. The magnetocaloric effect becomes particularly significant near the Curie temperature, the temperature at which a ferromagnetic material transitions from an ordered ferromagnetic phase to a disordered paramagnetic phase. Near this transition point, even small changes in magnetic field can produce substantial changes in magnetic entropy and temperature. This sensitivity arises because the magnetic moments are highly responsive to external stimuli in this temperature range. Consequently, many magnetocaloric materials are engineered so that their Curie temperature lies close to room temperature, enabling practical refrigeration systems. Magnetocaloric materials are also categorized based on the nature of their magnetic phase transitions. First-order magnetic transitions (FOMT) involve abrupt structural or magnetic changes and usually produce very large entropy changes and strong magnetocaloric effects. However, they may suffer from hysteresis losses and mechanical instability during repeated thermal cycles. In contrast, second-order magnetic transitions (SOMT) involve continuous changes in magnetic ordering and generally provide smaller entropy changes but offer greater stability and reversibility. Understanding the balance between these two transition types is critical for designing efficient and durable magnetocaloric cooling systems

*Corresponding author
Email: weizhang@ifm.tsinghua.edu.cn
DOI: 10.53533/JMA.v2i1.27

Types of Magnetocaloric Materials

Over the past several decades, researchers have developed a wide range of magnetocaloric materials with varying compositions, magnetic properties, and operating temperature ranges. These materials are typically classified into several major groups based on their elemental composition and magnetic phase behavior.

Rare-Earth Based Materials

Rare-earth elements have played a central role in the development of magnetocaloric materials due to their strong magnetic moments and favorable thermodynamic properties. Among these materials, gadolinium (Gd) is one of the most extensively studied magnetocaloric substances. Gadolinium exhibits a significant magnetocaloric effect near its Curie temperature of approximately 294 K, which is close to room temperature. This property makes it an ideal reference material for magnetic refrigeration research. Gadolinium and its alloys demonstrate relatively large entropy changes and moderate adiabatic temperature shifts when subjected to magnetic fields. Furthermore, they exhibit low magnetic hysteresis, allowing efficient and reversible magnetization cycles. Because of these advantages, gadolinium-based materials have been widely used in experimental magnetic refrigeration prototypes and laboratory studies. However, the high cost and limited availability of rare-earth elements have motivated researchers to search for alternative materials with comparable magnetocaloric performance but lower economic and environmental costs.

Transition-Metal Alloys

Transition-metal-based magnetocaloric materials have gained significant attention due to their relatively low cost and promising magnetocaloric properties. Compounds such as MnFeP-based alloys, Fe-Ni-Mn systems, and Mn-based intermetallic compounds exhibit large entropy changes and strong magneto-structural coupling. These materials often undergo first-order magnetic phase transitions that produce substantial temperature variations under moderate magnetic fields. One advantage of transition-metal alloys is their compositional flexibility. By adjusting the ratios of elements such as manganese, iron, phosphorus, and silicon, researchers can tailor the Curie temperature and optimize the magnetocaloric performance for specific temperature ranges. Many of these materials also exhibit high refrigeration capacities, making them suitable for practical cooling applications. Additionally, transition-metal alloys are generally more abundant and less expensive than rare-earth materials, which improves their potential for large-scale commercial deployment.

LaFeSi-Based Compounds

Among the most promising magnetocaloric materials for commercial refrigeration are $La(Fe,Si)_{13}$-based alloys. These materials exhibit giant magnetocaloric effects due to strong coupling between magnetic and structural transitions. One of their key advantages is the ability to adjust the Curie temperature through chemical substitution or hydrogenation, allowing precise control over the operating temperature range. LaFeSi compounds demonstrate large isothermal entropy changes and significant adiabatic temperature variations, making them highly effective for magnetic refrigeration systems operating near room temperature. Furthermore, their relatively low raw material cost and strong magnetocaloric performance have made them leading candidates for industrial magnetic cooling technologies. Research continues to focus on improving their mechanical stability, reducing hysteresis losses, and enhancing their durability under repeated thermal cycles.

Heusler Alloys

Heusler alloys, particularly those based on nickel, manganese, and other transition metals, represent another important class of magnetocaloric materials. These alloys often exhibit coupled magnetic and structural transformations known as martensitic phase transitions, which can produce very large entropy changes. Because of this combined magnetic and structural response, Heusler alloys are sometimes referred to as exhibiting a multicaloric effect, where magnetic, structural, and sometimes even electronic contributions enhance the overall cooling performance. Ni-Mn-based Heusler alloys have attracted considerable attention due to their tunable properties and large magnetocaloric responses. By modifying their chemical composition, researchers can adjust the transformation temperatures and optimize the magnetocaloric effect for specific cooling applications. However, these materials often experience thermal hysteresis and mechanical fatigue during repeated phase transitions, which can reduce their long-term reliability. Ongoing research focuses on improving their structural stability and minimizing energy losses during magnetization cycles. Together, these various classes of materials form the foundation of modern magnetocaloric research. Continued advances in materials engineering, nanostructuring, and computational materials science are expected to further enhance the performance of magnetocaloric materials and accelerate the development of efficient, environmentally friendly magnetic refrigeration technologies.

Magnetic Refrigeration Cycle

Magnetic refrigeration systems operate based on the magnetocaloric effect, and the most widely used operational mechanism is the Active Magnetic Regenerator (AMR) cycle. The AMR cycle integrates magnetocaloric materials with a heat transfer fluid and heat exchangers to produce continuous cooling. Unlike traditional vapor-compression refrigeration systems that depend on gaseous refrigerants, magnetic refrigeration uses solid magnetic materials to transfer heat between two reservoirs. This approach significantly reduces environmental impact because it eliminates the use of harmful refrigerant gases that contribute to ozone depletion and global warming. The first stage of the AMR cycle is magnetization. In this step, the magnetocaloric material is exposed to an external magnetic field generated by permanent magnets or electromagnets. The magnetic moments within the material align with the applied field, causing a decrease in magnetic entropy. Under adiabatic conditions, this reduction in entropy results in an increase in the material's temperature. As a consequence, the magnetocaloric material becomes warmer than the surrounding environment. This heating effect is the fundamental process that initiates the refrigeration cycle. Following magnetization, the system enters the heat transfer stage. During this step, the heat generated within the magnetocaloric material is transferred to a heat exchanger or circulating heat transfer fluid, typically water or a glycol-based solution. The fluid absorbs the excess heat from the material and transports it to the hot side of the refrigeration system. This process ensures that the magnetocaloric material returns close to its initial temperature before the next stage of the cycle begins. Efficient heat exchange is essential in this phase because it determines how effectively the system can remove heat from the material and maintain continuous operation. The third stage of the cycle is demagnetization, which occurs when the external magnetic field is removed or significantly reduced. When the magnetic field decreases, the magnetic moments in the material lose their alignment and return to a more disordered state. This process increases magnetic entropy and causes the material to cool below its initial temperature. The temperature drop is a direct manifestation of the magnetocaloric effect and represents the cooling phase of the cycle. Materials that exhibit large adiabatic temperature changes during demagnetization are particularly valuable for high-performance refrigeration systems. The final stage is heat absorption, where the cooled magnetocaloric material absorbs thermal energy from the environment or the object being cooled. In practical refrigeration systems, the cold side of the regenerator is placed in thermal contact with the space that needs cooling, such as a refrigerator compartment or electronic device. As the magnetocaloric material absorbs heat, it gradually returns to its original temperature, completing the thermodynamic cycle. The AMR cycle then repeats continuously as the magnetic field is periodically applied and removed. Through this repeated process, heat is effectively transferred from a cold reservoir to a hot reservoir without the need for traditional refrigerant fluids. The efficiency of magnetic refrigeration depends on several factors, including the strength of the applied magnetic field, the thermodynamic properties of the magnetocaloric material, and the design of the regenerator system. Advances in permanent magnet technology and regenerator engineering have significantly improved the performance of AMR-based systems. Researchers are also exploring rotating magnetic field configurations and multi-layer regenerator structures to enhance heat transfer efficiency and increase cooling capacity.

Technological Applications

Magnetocaloric cooling technologies have attracted considerable interest due to their potential to provide energy-efficient and environmentally sustainable refrigeration solutions. As global energy demand continues to grow, conventional cooling systems contribute significantly to electricity consumption and greenhouse gas emissions. Magnetic refrigeration offers an alternative approach that could reduce energy usage while eliminating harmful refrigerant gases. One of the most promising applications of magnetocaloric technology is domestic refrigeration. Household refrigerators and air-conditioning units currently rely on vapor-compression systems that use hydrofluorocarbon (HFC) refrigerants,

which have a high global warming potential. Magnetic refrigeration systems can operate without such gases, relying instead on solid magnetocaloric materials and magnetic fields. This makes them environmentally friendly and potentially more energy efficient. Research prototypes have already demonstrated compact magnetic refrigerators capable of operating near room temperature with competitive cooling performance. Another important application area is electronics cooling. Modern electronic devices, including high-performance processors, data centers, and power electronics, generate substantial amounts of heat during operation. Efficient thermal management is essential to maintain device performance and reliability. Magnetocaloric materials can provide localized cooling solutions that are compact, quiet, and energy efficient. Because magnetic refrigeration systems do not rely on compressors or moving refrigerant fluids, they can offer reduced mechanical noise and improved reliability in sensitive electronic environments. Magnetic refrigeration also plays a role in cryogenic cooling systems, particularly in scientific and medical applications. At extremely low temperatures, magnetic refrigeration techniques based on adiabatic demagnetization have been used for decades in low-temperature physics experiments. These systems are capable of achieving temperatures close to absolute zero, which are required for superconductivity studies, quantum computing experiments, and space instrumentation. In such applications, magnetocaloric cooling provides highly precise temperature control and stable thermal environments. In addition to domestic and scientific applications, magnetocaloric technology has potential in industrial refrigeration systems. Many industrial processes require large-scale cooling, including food processing, chemical manufacturing, and cold storage logistics. Magnetic refrigeration could improve energy efficiency in these sectors by reducing the electricity consumption associated with conventional refrigeration equipment. Furthermore, the absence of chemical refrigerants simplifies maintenance and reduces environmental risks associated with refrigerant leakage.

Challenges and Future Research Directions

Despite the significant progress made in magnetocaloric research, several challenges continue to limit the widespread commercialization of magnetic refrigeration technologies. One of the most critical issues is the high cost of magnetocaloric materials, particularly those based on rare-earth elements such as gadolinium. Rare-earth materials exhibit excellent magnetocaloric performance but are expensive and subject to supply chain limitations. Developing alternative materials composed of abundant and low-cost elements remains an important research priority. Another challenge involves the generation of strong magnetic fields required for effective refrigeration cycles. Magnetic refrigeration systems typically rely on permanent magnets or electromagnets to produce fields strong enough to induce significant temperature changes in magnetocaloric materials. While modern permanent magnets such as neodymium-iron-boron magnets can generate powerful fields, they also increase system cost and complexity. Designing magnetic circuits that maximize field strength while minimizing material usage is a key engineering challenge in magnetic refrigeration system development. Thermal hysteresis is another factor that can reduce system efficiency. Some magnetocaloric materials, particularly those exhibiting first-order magnetic phase transitions, show hysteresis effects during repeated magnetization and demagnetization cycles. Hysteresis leads to energy losses and reduces the reversibility of the magnetocaloric effect. Researchers are working to develop materials with minimal hysteresis while maintaining large entropy changes and strong magnetocaloric responses. Engineering design challenges also play a significant role in determining the performance of magnetic refrigeration systems. Efficient operation requires carefully optimized heat exchangers, regenerator structures, and fluid flow systems. The heat transfer fluid must effectively transport heat between the magnetocaloric material and the external environment while minimizing energy losses. Advanced regenerator designs, such as layered or micro-channel structures, are being investigated to enhance heat transfer efficiency and improve overall cooling capacity. Future research in magnetocaloric technology focuses on several key directions. Scientists are exploring new magnetocaloric materials, including transition-metal alloys and nanostructured compounds that provide strong magnetocaloric effects without relying on rare-earth elements. Computational materials science and machine learning techniques are increasingly used to predict and design materials with optimized magnetic and thermodynamic properties. Additionally, researchers are developing hybrid cooling systems that combine magnetocaloric materials with other caloric effects, such as electrocaloric and elastocaloric phenomena, to further enhance cooling efficiency. As advances in materials science, magnet design, and thermal engineering continue, magnetocaloric refrigeration is expected to become a viable alternative to conventional cooling technologies. With increasing global emphasis on energy efficiency and environmental sustainability, magnetic refrigeration systems have the potential to play an important role in the future of cooling technology.

Summary

Magnetocaloric materials represent a transformative approach to refrigeration technology. By exploiting the magnetocaloric effect, these materials enable solid-state cooling systems that are energy-efficient and environmentally sustainable. Significant progress has been made in developing materials with large entropy changes near room temperature, including rare-earth alloys, transition-metal compounds, and Heusler alloys. Although several engineering and economic challenges remain, advances in materials science and device design are expected to accelerate the commercialization of magnetic refrigeration systems. As global demand for energy-efficient cooling technologies continues to rise, magnetocaloric materials are likely to play an important role in next-generation thermal management and sustainable energy solutions.

References

[1] Gschneidner, K., & Pecharsky, V. (2000). Magnetocaloric materials. Annual Review of Materials Science.
[2] Tishin, A. M., & Spichkin, Y. I. (2016). The Magnetocaloric Effect and Its Applications.
[3] Franco, V., et al. (2018). Magnetocaloric effect: From materials research to refrigeration devices.
[4] Pecharsky, V., & Gschneidner, K. (1999). Giant magnetocaloric effect.
[5] Mellari, S. (2023). Introduction to magnetic refrigeration.
[6] Lucia, U. (2024). Magnetocaloric refrigeration and sustainability.
[7] Vinod, A. (2024). Evolution of LaFeSi magnetocaloric materials.
[8] Ayaş, A. (2023). Magnetic refrigeration research progress.
[9] Belo, J. H. (2019). Magnetocaloric materials from micro- to nanoscale.
[10] Warburg, E. (1881). Discovery of magnetocaloric effect.
[11] Brown, G. (1976). Magnetic refrigeration near room temperature.
[12] Tegus, O., et al. (2002). Transition-metal-based magnetic refrigerants.